



- Print speeds up to 8 ips (format & carrier dependent)
- Prints on paper & polypropylene labels and tags
- Good smudge & scratch resistance
- Prints at moderate print head energy heat settings

TECHNICAL DATA

RIBBON PROPERTY

Base Material	Polyester Film
Ink Color	Black
Transmission Density	2.1
Back Coating	Yes
Total Thickness	< 9 µm
PET Thickness	4.5 µm
Optical Density	1.6
Ink Melt Point	167°F (75°C)
Recommended Substrates	Coated and uncoated paper, tag stocks, and synthetics

DURABILITY OF PRINTED IMAGE

Smudge & Scratch Resistance	Good
Storage Conditions	40-90°F (5-35°C), 20-80% RH
Storage Life	1 year after manufacturing

APPLICATION FIELDS

Inventory, Shipping, Pharmaceutical, Cosmetics, Shelf-edge, Markdown, Lawn and Garden, Ingredient, Food Rotation, Work In Process, Rating Plates, Retail Labeling, Care Labels, Signage & Logos, Laboratory, Healthcare, Tags, Short Term Outdoor Applications, Conveyor Sorting, Chemical Drums

Please contact us if your application is not among these.

The above data represents product averages, allowing for industry accepted variances. These products should be tested in the end-use conditions to ensure that they meet the requirements of the specific application. Specification may change without notice.

SATO AMERICA CORPORATE

14125 South Bridge Circle
Charlotte, NC 28273

Phone: (704) 644-1650

sales-sal@sato-global.com

LABEL MANUFACTURING, SERVICE & SALES

UNITED STATES MEXICO CENTRAL AMERICA
CANADA CARIBBEAN

9007036



www.satoamerica.com

©2022 SATO America. All rights Reserved. Rev A • Any unauthorized reproduction of this content, in part or whole, is strictly prohibited • SATO is a registered trademark of SATO Corporation and its subsidiaries in Japan, the U.S. and other countries. All other trademarks are the property of their respective owners.