

**T113** Thermal Ribbon | Wax-Resin Near Edge



- Print speeds up to 12 ips (format & carrier dependent)
- Prints on a wide variety of media
- High smudge & scratch resistance
- Prints at moderate print head energy heat settings

## **TECHNICAL DATA**

RIBBON PROPERTY	
Base Material	Polyester Film
Ink Color	Black
Transmission Density	1.95
Back Coating	Yes
Total Thickness	Black < 8 µm Anti static build-up treated
PET Thickness	4.5 μm
Optical Density	≥ 2.3 D
Ink Melt Point	176°F (80°C)
Recommended Substrates	Coated and uncoated paper, coated tag stocks, and synthetics
DURABILITY OF PRINTED IMAGE	
Smudge & Scratch Resistance	High
Storage Condition	40°-90°F (5-35°C), 20-85% RH
Storage Life	1 year after manufacturing

Inventory, Shipping, Pharmaceutical, Cosmetics, Shelf-edge, Markdown, Lawn and Garden (Pot tags, Hang Tags, Slip-on End to End Tags), Ingredient, Food Rotation, Work In Process, Rating Plates, Retail Labeling, Care Labels, Signage & Logos, Laboratory, Healthcare, Tags, Short Term Outdoor Applications, Conveyor Sorting, Chemical Drums

Please contact us if your application is not among these.

The above data represents product averages, allowing for industry accepted variances. These products should be tested in the end-use conditions to ensure that they meet the requirements of the specific application. Specification may change without notice.



SATO AMERICA CORPORATE

14125 South Bridge Circle Charlotte, NC 28273 Phone: (704) 644-1650 sales-sal@sato-global.com LABEL MANUFACTURING, SERVICE & SALES UNITED STATES MEXICO CENTRAL AMERICA CANADA CARIBBEAN

## www.satoamerica.com

©2022 SATO America . All rights Reserved. Rev A • Any unauthorized reproduction of this content, in part or whole, is strictly prohibited • SATO is a registered trademark of SATO Corporation and its subsidiaries in Japan, the U.S. and other countries. All other trademarks are the property of their respective owners.